

# SELLEYS®

## PRO-TRADE

### JOINT SEALANT FC



**HIGH STRENGTH, MULTIPURPOSE FAST CURE POLYURETHANE ADHESIVE AND FLEXIBLE JOINT SEALANT**

- Fast cure polyurethane
- High flexibility with  $\pm 25\%$  joint movement
- Excellent resistance to aging and weathering
- Cures bubble free
- No shrinkage during curing
- Excellent adhesion on common building materials
- Suitable for internal and external vertical and horizontal applications.

| PRODUCT CODE | BARCODE       | COLOUR  | SIZE  | CARTON QTY | LAYER QTY | PALLET QTY |
|--------------|---------------|---------|-------|------------|-----------|------------|
| 102116       | 9300697130051 | ■ WHITE | 310ML | 12         | 432       | 1728       |
| 102117       | 9300697130068 | ■ GREY  | 310ml | 12         | 432       | 1728       |
| 102118       | 9300697130075 | ■ BLACK | 310ml | 12         | 432       | 1728       |
| 102119       | 9300697130082 | ■ WHITE | 600ml | 12         | 192       | 960        |
| 102120       | 9300697130099 | ■ GREY  | 600ml | 12         | 192       | 960        |
| 102121       | 9300697130105 | ■ BLACK | 600ml | 12         | 192       | 960        |

| PROPERTY                              | TYPICAL RESULT                |
|---------------------------------------|-------------------------------|
| Technology                            | Polyurethane                  |
| Colour                                | White, Grey and Black         |
| Density                               | 1.08 $\pm$ 0.03 g/ml          |
| Application Temperature               | 5°C - 40°C                    |
| Tack-Free Time (23°C / 50% RH)        | 40 $\pm$ 10 minutes           |
| Cure Rate (23°C / 50% RH)             | Min. 3 mm/24h                 |
| Sagging (EN ISO 7390)                 | 0 mm                          |
| Tensile Strength (ISO 37)             | 2.0 - 2.5 N/mm <sup>2</sup>   |
| Elongation at Break (ISO 37)          | $\geq$ 400%                   |
| Shore A Hardness (ISO 868)            | 40 $\pm$ 5                    |
| Modulus at 100% Elongation (ISO 8339) | 0.35 - 0.40 N/mm <sup>2</sup> |
| Movement Capability                   | +/- 25%                       |
| Service Temperature                   | - 40°C / +70°C                |

Indicative data only, not intended for preparation of specifications

**IF IT'S SELLEYS IT WORKS®**